

Product Description

Topilene® J346F is a specially designed polypropylene block copolymer that features very high impact strength and excellent optical properties. It is suitable for retort CPP film extrusion. **Topilene® J346F** complies with FDA 21 CFR 177.1520 and EU No 10/2011 for food contact.

Characteristics

Typical Application Retort CPP film / Cast Film

Features High Stiffness / High Impact Strength / Excellent Heat Resistance / Low Fisheye / Good Heat Seal Strength

Typical Properties

| Resin Properties | Method | Value | Unit |
|------------------------------------|------------|--------|--------------------|
| Melt Index(230°C, 2.16kg) | ASTM D1238 | 2.5 | g/10min |
| Density | ASTM D792 | 0.9 | g/cm ³ |
| Tensile Strength at Yield | ASTM D638 | 300 | kg/cm ² |
| Flexural Modulus | ASTM D790 | 13,300 | kg/cm ² |
| Notched Izod Impact Strength(23°C) | ASTM D256 | 12 | kg-cm/cm |
| Rockwell Hardness | ASTM D785 | 90 | R-Scale |
| Heat Deflection Temperature | ASTM D648 | 110 | °C |
| Vicat Softening Point | ASTM D1525 | 150 | °C |
| Haze(40 μm CPP film) | ASTM D1003 | 69 | % |

The values listed above are typical values for reference purpose only and shall not be construed as specifications.

Storage and Handling

This product should be stored in dry condition at temperature below 40°C and protected from UV-light. When condensation is visible or can be expected, pre-drying is recommended. (Drying condition: 80~100°C/2~4hours at air circulated condition)

Disclaimer

All information, including product characteristics, applications and properties are for reference purpose only and shall not be construed as specifications. Before using this product, customers should carefully review the instructions for use of the product to determine whether the product is suitable for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of this product. HYOSUNG CHEMICAL CORPORATION assumes no legal responsibility or liability for the contents of this document. We reserve the right to change the contents of this document without prior notice. This document is copyrighted by HYOSUNG CHEMICAL CORPORATION. **Topilene®** is a registered trademark owned or used by HYOSUNG CHEMICAL CORPORATION.

Contacts

Head Office 235, Banpo-daero, Seocho-gu, Seoul, Korea 06578

Tel: +82-2-2146-5451~9 Fax: +82-2-2146-5428

Online www.hyosungchemical.com

www.topilene.com

