

Topilene® HJ801R Polypropylene Homopolymer

For Small Home Electronic Appliances

Product Description

Topilene® HJ801R is a specially designed high isotactic polypropylene homopolymer that features high stiffness, high flowability and excellent long term heat stability. It is suitable for small home electronic appliances. **Topilene® HJ801R** complies with FDA requirements in the code of Federal Regulations in 21 CFR 177.1520 for food contact. It complies with UL Standard for Safety for Polymeric Materials – Long Term Property Evaluations, UL 746B.

Characteristics

Typical Application Small home electronic appliances(Toasters, Coffee makers, Steam irons, etc)

Features Long-term heat resistance(UL 94HB, 746B) / High stiffness / Excellent surface hardness / High crystallization temperature (Short Cycle Time)

Typical Properties

Resin Properties	Method	Value	Unit
Melt Index(230°C, 2.16kg)	ASTM D1238	13	g/10min
Density	ASTM D792	0.90	g/cm ³
Tensile Strength at Yield	ASTM D638	420	kg/cm ²
Flexural Modulus	ASTM D790	21,500	kg/cm ²
Notched Izod Impact Strength(23°C)	ASTM D256	3.5	kg-cm/cm
Rockwell Hardness	ASTM D785	110	R-Scale
Heat Deflection Temperature	ASTM D648	140	°C
Vicat Softening Point	ASTM D1525	155	°C

The values listed above are typical values for reference purpose only and shall not be construed as specifications.

Storage and Handling

This product should be stored in dry condition at temperature below 40°C and protected from UV-light. When condensation is visible or can be expected, pre-drying is recommended. (Drying condition: 80~100°C/2~4hours at air circulated condition)

Disclaimer

All information, including product characteristics, applications and properties are for reference purpose only and shall not be construed as specifications. Before using this product, customers should carefully review the instructions for use of the product to determine whether the product is suitable for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of this product. HYOSUNG CHEMICAL CORPORATION assumes no legal responsibility or liability for the contents of this document. We reserve the right to change the contents of this document without prior notice. This document is copyrighted by HYOSUNG CHEMICAL CORPORATION. **Topilene®** is a registered trademark owned or used by HYOSUNG CHEMICAL CORPORATION.

Contacts

Head Office 235, Banpo-daero, Seocho-gu, Seoul, Korea 06578

Tel: +82-2-2146-5451~7 Fax: +82-2-2146-5428

Online www.hyosungchemical.com

www.topilene.com

